

## Fenomastic My Home Rich Matt

**Surface:** Plaster/CMU/Concrete/Gypsum Board Partition

### Primer Coat

One coat: Jotun Fenomastic Emulsion Primer:

Vol. solids: 25±2 %

### Filler Coat

Two coats: Jotun Stucco:

Vol. solids: 50 ±2%

### Topcoats

Two coats: Jotun Fenomastic My Home Rich Matt

Vol. solids are 40 ± 2%

### Properties

- **VOC content**  
23.9 g/l (US EPA 24)
- **Washability/Scrub Resistance**  
>10,000 scrubs (DIN 53778)
- **Hazardous Materials**  
Free from:
  - Heavy Metals (ICP-AES)
  - APEO (BS 3762:90)
  - Formaldehyde (UV Spectroscopy)
  - Pthalates (GCMS)
- **Burnish Resistance**  
Gloss Change:  
60° =0.1units  
85° =0.9 units
- **Polish Resistance**  
Gloss change:  
@ 60 = 0.4 units  
@ 85 = 6.9 units
- **Contrast Ratio/whiteness**  
97.00/94.82 (ASTM D2805-88)
- **Practical Washability:**  
Rating 0-2: (ASTM D4828:94) (0 = All stains removed & 2 = No stains removed)
- **Colour rub off:**  
Class A (Class A = Best & Class E = Worst)